

DATA SHEET 22VW0.100.35900

## SIVW

White glossy self-adhesive PVC film with paper backing. Suitable for labels, posters, displays and exhibition panels.

### Printing Systems



### Rolls

Art.Number	Width (mm)	Thickness	Length (m)
22VW0.100.34000	430	0.110 mm	20
22VW0.100.35900	610	0.110 mm	20
22VW0.100.39000	914	0.110 mm	20
22VW0.100.30500	1067	0.110 mm	20
22VW0.100.32000	1270	0.110 mm	20
22VW0.100.33300	1370	0.110 mm	20
22VW0.100.35000	1520	0.110 mm	20

### Technical data

#### Characteristic

- High brilliance of colours
- Permanent self adhesive
- Universal use

#### Finish

- self-adhesive with paper backing
- White glossy

## Specifications

Release liner	siliconized paper ~ 0.145 mm
Width (mm)	610
Thickness base material with inkjet coating	0.110 mm
Core Diameter	50 mm
Adhesion strength	~ 3.5.N / 25 mm (A.F.E.R.A.), after 24 h ~ 10 N / 25 mm (A.F.E.R.A.)
Type of adhesive	polyacrylate dispersion
Length (m)	20
Base Material	calendered monomeric plasticized PVC, 0.100 mm
Total thickness	0.260 mm
Packing quantity	1 roll

## Compatibility

- Suitable for most Ink Jet plotters using dye- or pigmented inks

## Handling

- Laminating: The printed surface must be protected with foils for cold lamination if it is subject to humidity, sweaty hands, abrasion or any other influences. For a short term outdoor use, SIVW must always be protected with a 5mm overlapping lamination.
- Gluing: SIVW will stick to any solid, smooth surfaces which are dry and free of dirt, grease, silicon etc. Before gluing it is absolutely necessary to check that the surface is appropriate to this aim and that it has been prepared (cleaned) professionally. During gluing the temperature must reach at least 15°C. You can remove SIVW by heating the film's surface with a hot air gun. Then pull it off carefully.

## Storage

- Shelf life: 1 year after delivery
- After printing the remaining roll must be removed from the plotter and stored in its closed original packing in a cool and dry environment.

## Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.