

DATA SHEET 48244.130.xxxxx

GO-AG DES

Polyester film with anti glare coating and UV protection on the front side suitable for window and structure printing with 2 component lacquers. Reverse side with coating for digital printing with eco-solvent Inkjet.

Material is available with a thickness of 0.13 mm and 0.18 mm. Available in sheets and rolls. Sheets available in standard packing unit or on demand. All sheets are equipped with interleaving paper as standard. Options such as self-adhesive protective film is available but will be an additional cost.

Formats

Art.Number	Nominal thickness (mm)	Packing quantity
48244.130.xxxxx	0.13	100
48244.180.xxxxx	0.18	100

Rolls

Art.Number	Length (m)	Nominal thickness (mm)
48244.130.xxxxx	100	0.13
48244.180.xxxxx	100	0.18

Technical data

Characteristic



- Suitable for eco solvent ink
- Suitable for Ink Jet digital
- Ink receptive coating
- Suitable for window printing
- Suitable for textured laquers
- With UV protection

Specifications

Nominal thickness (mil)	5.2
Nominal thickness (mm)	0.13
Base Material	Polyester
Packing quantity	100

Product Applications

Handling

- Preliminary testing necessary by customer

Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60%.
- Shelf life 1 year after delivery (under above storage conditions)

Properties

Property	Test Method	Value
Optical		
Haze	ASTM D1003-77	15 - 25%
Gloss level (60°)	ASTM D2457-70, ASTM D523	45 - 65 GU
Mechanical		
Embossing	Fofox method	possible
Tensile strength at break	ASTM D 882	170 N/mm ²
Switch life	Fofox method according to DIN 42115	> 5 Mio. flexes
Chemical		
Chemical stability	Fofox method	good
Electrical		
Dielectric strength ¹	ASTM D149-81	120 kV/mm (125 µm)
Thermal		
Shrinkage TD	130°C 30 min Fofox method	< 0,7%
Shrinkage MD	130°C 30 min Fofox method	< 0,7%
Maximum processing temperature		120°C
Melting temperature ¹	ASTM E794-85	255°C
Surface		
Roughness Ra	EN ISO 4287, ASME B46.1	0,7 - 0,9 µm
Scratch resistance	Fofox method	good
Surface tension front side	DIN 53364, ASTM D2578	28 - 35 mN/m

Surface tension reverse side

DIN 53364, ASTM D2578

38 - 41 mN/m

¹ Data derived from base film Polyester manufacturer's literature

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

