

DATA SHEET 48054.130.xxxxx

## GO-MA/2K ESD

Polyester film with matt and conductive coating on the front side. The specific surface resistance of  $10^6$  to  $10^9$  ohm/square (DIN 53482) allows slow release without lightning discharge. Reverse side with ink receptive coating. Material is available with a thickness of 0.13 or 0.18 mm.

Available in sheets and rolls. Sheets available in standard packing unit or on demand. All sheets are equipped with interleaving paper as standard. Options such as self-adhesive protective film is available but will be an additional cost.

### Formats

Art.Number	Nominal thickness (mm)	Packing quantity
48054.130.xxxxx	0.13	100
48054.180.xxxxx	0.18	100

### Rolls

Art.Number	Length (m)	Nominal thickness (mm)
48054.130.xxxxx	100	0.13
48054.180.xxxxx	100	0.18

### Technical data

#### Characteristic



- Ink receptive coating
- Suitable for window printing
- No lightning discharge

#### Specifications

Nominal thickness (mil)	5.2
Nominal thickness (mm)	0.13

Base Material	Polyester
Packing quantity	100

## Product Applications

### Handling

- Preliminary testing necessary by customer

### Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60 %
- Shelf life 1 year after delivery (under above storage conditions)

## Properties

Property	Test Method	Value
<b>Optical</b>		
Haze	ASTM D1003-77	90 - 95%
Gloss level (60°)	ASTM D2457-70, ASTM D523	6 - 7 GU
<b>Mechanical</b>		
Embossing	Folex method	possible
Tensile strength at break	ASTM D 882	170 N/mm <sup>2</sup>
Switch life	Folex method according to DIN 42115	> 5 Mio. flexes
<b>Chemical</b>		
Chemical stability	Folex method	good
<b>Electrical</b>		
Dielectric strength <sup>1</sup>	ASTM D149-81	120 kV/mm (125 µm)
Dielectric constant <sup>1</sup>	ASTM D150, 1 kHz	3,25 (23my)
Surface resistivity	ASTM D257-83	10 <sup>6</sup> - 10 <sup>9</sup> Ohm/sq.
<b>Thermal</b>		
Shrinkage TD	130°C 30 min Folex method	< 0,7%
Shrinkage MD	130°C 30 min Folex method	< 0,7%
Maximum processing temperature		120°C
Melting temperature <sup>1</sup>	ASTM E794-85	255°C
<b>Surface</b>		
Roughness Ra	EN ISO 4287, ASME B46.1	0,8 - 1,1 µm
Scratch resistance	Folex method	good
Surface tension front side	DIN 53364, ASTM D2578	44 ± 2 mN/m
Surface tension reverse side	DIN 53364, ASTM D2578	38 ± 2 mN/m

<sup>1</sup> Data derived from base film Polyester manufacturer's literature for base film

**Product liability clause**

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

