

## DATA SHEET 4891x.125.xxxxx

## EL-NG

Polyester film with conductive coating on the front side. Both sides with ink receptive coating. Material is available with a thickness of 0.13 mm and 0.18 mm.

Available in sheets and rolls. Sheets available in standard packing unit or on demand. All sheets and rolls are equipped with self-adhesive protective film on the conductive side as standard.

## Formats

Art.Number	Nominal thickness (mm)	Packing quantity
4891x.125.xxxxx	0.13	100
4891x.175.xxxxx	0.18	100

## Rolls

Art.Number	Length (m)	Nominal thickness (mm)
4891x.125.xxxxx	100	0.13
4891x.175.xxxxx	100	0.18

## Technical data

## Characteristic



- Ink receptive coating
- Suitable for textured laquers

## Specifications

Nominal thickness (mil)	5.2
Nominal thickness (mm)	0.13
Base Material	Polyester
Packing quantity	100

## Handling

- Preliminary testing necessary by customer

## Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60 %
- Shelf life 1 year after delivery (under above storage conditions)

## Properties

Property	Test Method	Value
<b>Optical</b>		
Haze	ASTM D1003-77	0,6 - 2,0%
<b>Mechanical</b>		
Embossing	Folex method	possible
Tensile strength at break	ASTM D 882	170 N/mm <sup>2</sup>
<b>Chemical</b>		
Chemical stability	Folex method	partly resistant
<b>Electrical</b>		
Dielectric strength <sup>1</sup>	ASTM D149-81	120 kV/mm (125 µm)
Surface resistivity	ASTM D257-83	110 Ohm/sq.
<b>Thermal</b>		
Shrinkage TD	130°C 30 min Folex method	< 0,7%
Shrinkage MD	130°C 30 min Folex method	< 0,7%
Maximum processing temperature		120°C
Melting temperature <sup>1</sup>	ASTM E794-85	255°C
<b>Surface</b>		
Roughness Ra	EN ISO 4287, ASME B46.1	0,1 - 0,4 µm
Scratch resistance	Folex method	partly resistant
Surface tension Front side	DIN 53364, ASTM D2578	44 ± 2 mN/m
Surface tension Back side	DIN 53364, ASTM D2578	38 ± 2 mN/m

<sup>1</sup> Data derived from base film Polyester manufacturer's literature

### Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

