

DATA SHEET 03508.310.44200

Fine Art Paper Contour

A top coated matt archival artist paper with a subtle texture which is made from 100% cellulose, for producing high quality fine art reproductions or fine art photography. The coating ensures stunningly brilliant colours with superb flatness with high density blacks. Ideal for classic paintings.

Printing Systems



Formats

Art.Number	Basic weight (g)	Format	Packing quantity
03508.310.44200	310	A4	25

Technical data

Characteristic

- Neutral Colour image reproduction
- Very finely defined prints
- Suitable for Ink Jet printer
- Good ink absorption
- Excellent outstanding durability of the prints when using pigmented inks
- Matt white fine art paper, acid-free, on 100% cellulose base
- Excellent outstanding durability of the prints when using pigmented inks Characteristic
- Saturated black and white and colour prints
- Instant dry

Finish

- White matt, smooth structured surface

Specifications

Basic weight (g)	310
Basic weight (oz)	10.94
Coating Printsides	Ink Jet
Width (inch)	8.27
Width (mm)	210
Printside	Slightly tacky side
Format	A4
Length (inch)	11.69
Length (mm)	297
Base Material	Fine Art Paper
Packing quantity	25

Compatibility

- For use on most small format Ink Jet printers such as: HP, Canon, Epson, Apple, Digital, Kodak, Lexmark, Olivetti, Tektronix, Xerox, etc.

Handling

- Between 15-30°C and 30-70% r.h.
- Printer mode: fine art paper, mat coated paper o.s.
- A preconditioning period of 24 hours within the printing environment is recommended.
- Please follow the handling instructions supplied with this product as well as the Ink Jet Printer manufacturers manual.
- Ink Load: approx. 260 - 300% (may vary according to ink system and RIP calibration).
- Avoid moisture and fingerprints.

Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60%.
- Shelf life: 1 year after delivery
- Store in a cool and dry place

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.