

DATA SHEET 29729.180.44800

BG-72 WO

Glossy white film for colour laser printers. Folex BG-72 WO provides brilliant, true view-on presentations and can be used as an universal colour toner film. This glossy white film carries the same coatings on both sides and is available in a variety of different thicknesses.

Printing Systems



Formats

Art.Number	Format	Nominal thickness (mm)	Packing quantity
29729.125.44100	A4	0.125	50
29729.125.44800	A4	0.125	500
29729.125.43100	A3	0.125	50
29729.125.41800	A3	0.125	500
29729.180.44000	A4	0.180	100
29729.180.44800	A4	0.180	500
29729.180.43100	A3	0.180	50
29729.250.44100	A4	0.250	50
29729.250.43100	A3	0.250	50

Technical data

Characteristic



- True colour
- Fibre free
- Also suitable for machines with high fixing temperature
- Excellent runnability
- Good flatness

- Excellent toner bonding
- Heat resistant
- Highly universal
- Tear resistant
- Splash resistant

Finish

- White glossy

Specifications

Coating Printsides	Laser & Copier colour
Width (inch)	8.27
Width (mm)	210
Printsides	Printable both sides
Format	A4
Length (inch)	11.69
Length (mm)	297
Nominal thickness (mil)	7.2
Nominal thickness (mm)	0.180
Base Material	Polyester film
Packing quantity	500

Compatibility

- For use on most Mono & Colour Laser Printers.

Handling

- Please follow the handling instructions supplied with this product as well as the Copier / Printer manufacturers manual.
- Avoid moisture and fingerprints.

Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60 %
- Store in a cool and dry place
- Shelf life 1 year after delivery (under above storage conditions)

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the

complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.