

DATA SHEET 31300.125.43100

X-130

Coating suitable for dry toner copiers with excellent universal properties The Folex X-130 Series is a super heat-treated film for copiers with very high fusing temperatures ensuring excellent flatness properties.

Printing Systems



Formats

| Art.Number | Format | Nominal thickness (mm) | Packing quantity |
|-----------------|--------|------------------------|------------------|
| 31300.125.44000 | A4 | 0.125 | 100 |
| 31300.125.43100 | A3 | 0.125 | 50 |

Technical data

Characteristic



- Also suitable for machines with high fixing temperature
- Excellent runnability
- Good flatness
- Excellent toner bonding
- Heat resistant

Finish

- High Heat
- Clear transparent

Specifications

| | |
|-------------------------|----------------------|
| Coating Printsideside | Copier mono |
| Width (inch) | 11.69 |
| Width (mm) | 297 |
| Printside | Printable both sides |
| Format | A3 |
| Length (inch) | 16.54 |
| Length (mm) | 420 |
| Nominal thickness (mil) | 5 |
| Nominal thickness (mm) | 0.125 |
| Base Material | Polyester film |
| Packing quantity | 50 |

Compatibility

- For use on Mono Copiers.

Handling

- Please follow the handling instructions supplied with this product as well as the machine manufacturers manual.
- Avoid moisture and fingerprints.

Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60%.
- Shelf life 1 year after delivery (under recommended storage conditions)
- Store in a cool and dry place

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.