

DATA SHEET 48264.130.xxxxx

GO-AG DUV (DISCONTINUED PRODUCT)

Polyester film with anti glare coating on the front side suitable for window and structure printing with 2 component lacquers. Reverse side with coating for digital printing with UV Inkjet. Material is available with a thickness of 0.13 mm.

Available in sheets and rolls. Sheets available in standard packing unit or on demand. All sheets are equipped with interleaving paper as standard. Options such as self-adhesive protective film is available but will be an additional cost.

Formats

Art.Number	Nominal thickness (mm)	Packing quantity
48264.130.xxxxx	0.13	100

Rolls

Art.Number	Length (m)	Nominal thickness (mm)
48264.130.xxxxx	100	0.13

Technical data

Characteristic



- Suitable for Ink Jet digital
- Ink receptive coating
- Suitable for window printing
- Suitable for textured lacquers
- Suitable for selected UV-coatings

Specifications

Nominal thickness (mil)	5.2
Nominal thickness (mm)	0.13
Base Material	Polyester

Packing quantity 100

Product Applications

- Suitable for Membrane Switches, sign production as well as for production of labels
- Useable on most large format Ink Jet printers using UV curing ink systems.

Handling

- Preliminary testing necessary by customer

Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60 %
- Shelf life 1 year after delivery (under above storage conditions)

Properties

Property	Test Method	Value
Optical		
Haze	ASTM D1003-77	15 - 25%
Gloss level (60°)	ASTM D2457-70, ASTM D523	45 - 65 GU
Mechanical		
Embossing	Folex method	possible
Tensile strength at break	ASTM D 882	170 N/mm ²
Switch life	Folex method according to DIN 42115	> 5 Mio. flexes
Chemical		
Chemical stability	Folex method	good
Electrical		
Dielectric strength ¹	ASTM D149-81	120 kV/mm (125 µm)
Thermal		
Shrinkage TD	130°C 30 min Folex method	< 0,7%
Shrinkage MD	130°C 30 min Folex method	< 0,7%
Maximum processing temperature		120°C
Melting temperature ¹	ASTM E794-85	255°C
Surface		
Roughness Ra	EN ISO 4287, ASME B46.1	0,7 - 0,9 µm
Scratch resistance	Folex method	good
Surface tension front side	DIN 53364, ASTM D2578	28 - 35 mN/m
Surface tension reverse side	DIN 53364, ASTM D2578	41 - 44 mN/m

¹ Data derived from base film Polyester manufacturer's literature

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.