

DATA SHEET 17067.190.32000

Folarex HS 2x Matt

This polyester drawing film has been developed specifically for manual drawing and features an extremely fine, antistatic matt surface. It satisfies the highest requirements when drawing using China inks. The extremely fine surface produces sharp ink lines which do not spread. Any ink lines can be easily and completely removed using a moistened China ink eraser. Going over the corrected area again with a pencil eraser will produce a surface that can be redrawn without any problem.

Rolls

Art.Number	Width (mm)	Length (m)	Base Thickness(μm)
17063.070.32000	1220	20	70
17064.090.32000	1220	20	90
17066.140.32000	1220	20	140
17067.190.32000	1220	20	190

Technical data

Characteristic

- Anti-static
- Super sharp edge definition
- Environmental friendly

Finish

- Matt Translucent Surface

Specifications

Coating Printsideside	Technical Bureau
Width (mm)	1220
Printside	Identical coating
Length (m)	20
Base Thickness(μm)	190
Base Material	Polyester film

Compatibility

- Use with ink, graphite, pencils and polymer plastic mines. Pen plotter with not too high drawing speed.
- For use on most Large Format Mono Copiers and Laser Plotters, Pen Plotters, Laser Printers. Also for Offset & Serigraphy.
- For use on most Pen Plotters.

Handling

- Please follow the special handling instructions (instruction sheet).
- Between 15-30°C and 30-70% r.h.
- A preconditioning period of 24 hours within the printing environment is recommended.
- For correct feeding please follow the equipment suppliers manual.
- Avoid moisture and fingerprints.

Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60 %
- Store in a cool and dry place

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.