

DATA SHEET 29738.140.44800

Longlife Pro Matt WO

Longlife Pro Matt WO provides brilliant, vibrant images onto tear free, white polyester film which does not require lamination. This attractive matt white film is ideal for long life, archival applications and as a universal colour toner film. It has the same printable coating on both sides and is available in a variety of different thicknesses. To produce durable manuals, outdoor signs, Point of Sale, Point of Purchase, charts, maps, signage, menu cards, etc.

Printing Systems



Formats

Art.Number	Format	Nominal thickness (mm)	Packing quantity
29738.090.44000	A4	0.090	100
29738.090.44900	A4	0.090	1.000
29738.090.43100	A3	0.090	50
29738.115.44000	A4	0.115	100
29738.115.44800	A4	0.115	500
29738.115.43100	A3	0.115	50
29738.140.44000	A4	0.140	100
29738.140.44800	A4	0.140	500
29738.140.43100	A3	0.140	50
29738.190.44000	A4	0.190	100
29738.190.44800	A4	0.190	500
29738.190.43100	A3	0.190	50
29738.265.44100	A4	0.265	50
29738.265.44800	A4	0.265	500
29738.265.43100	A3	0.265	50
29738.350.44100	A4	0.350	50
29738.350.44700	A4	0.350	250
29738.350.43100	A3	0.350	50

Technical data

Characteristic



- True colours, printable both sides
- Excellent light resistance
- Fibre free
- Also suitable for machines with high fixing temperature
- Excellent runnability
- Excellent toner bonding
- Heat resistant
- Highly universal
- Can be die-cut/punched (after printing)
- Tear resistant
- Splash resistant

Finish

- White matt

Specifications

Coating Printsides	Laser & Copier colour
Width (mm)	210
Printsides	Printable both sides
Format	A4
Length (mm)	297
Nominal thickness (mil)	5.6
Nominal thickness (mm)	0.140
Base Material	Polyester film
Packing quantity	500

Compatibility

- For use on most Mono & Colour Laser Printers.

Handling

- Please follow the handling instructions supplied with this product as well as the Copier / Printer manufacturers manual.
- Avoid moisture and fingerprints.

Storage

- Shelf life 1 year after delivery (under above storage conditions)
- Store in the closed original packaging in a cool and dry place at a room temperature of 15 - 25°C and at a humidity of 30 - 60%.

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.