

DATA SHEET 45421.180.xxxxx

## GO-HC NQ

Clear polyester film with scratch resistant coating on the front side suitable for structured printing with UV lacquers. High UV-stability. The reverse side has an ink receptive coating.

Material is available with a thickness of 0.13 mm and 0.18 mm.

GO-HC \*New Version\* replaces the product GO-HC NQ.

Available in sheets and rolls. Sheets available in standard packing unit or on demand. All sheets and rolls are equipped with blue self-adhesive protective film on the reverse side as standard. If the second side is covered as well with protection film this film will be transparent.

### Formats

Art.Number	Nominal thickness (mm)	Packing quantity
45421.130.xxxxx	0.13	100
45421.181.xxxxx	0.18	100

### Rolls

Art.Number	Length (m)	Nominal thickness (mm)
45421.130.xxxxx	100	0.13
45421.180.xxxxx	100	0.18

### Technical data

#### Characteristic



- Ink receptive coating
- Suitable for textured lacquers
- Suitable for selected UV-coatings
- With UV protection

Excellent chemical resistance to common industrial solvents and household chemicals - please refer to Folex "Chemical Resistance Datasheet".

Folex products can be printed digital and screen in many cases with excellent results. We offer improved versions dedicated for digital printing.

### Specifications

Length (m)	100
Nominal thickness (mil)	7.2
Nominal thickness (mm)	0.18
Base Material	Polyester

### Product Applications

- Suitable for Membrane Switches, sign production as well as for production of labels

### Storage

- Once packaging is opened, store at a room temperature of 15 - 25°C and at a humidity of 30 - 60 %
- Shelf life 1 year after delivery (under above storage conditions)

### Properties

Property	Test Method	Value
Thickness	Folex method	0.13 - 0.14 mm (0,13 mm), 0.18 - 0.19 mm (0,18 mm)
<b>Optical</b>		
Haze	ASTM D1003-77	0,3 - 1,5%
Gloss level (20°)	ASTM D2457-70, ASTM D523	165 - 175 GU
Total luminous transmission	ASTM D1003-77	89 - 93%
Yellowness Index	DIN 6167	1.02 (0,13 mm), 1.08 (0,18 mm)
<b>Mechanical</b>		
Embossing	Folex method	possible
Tensile strength at break <sup>1</sup>	ASTM D 882	170 N/mm <sup>2</sup>
Switch life	Folex method according to DIN 42115	> 5 Mio. flexes
Abrasion test	Folex method	Delta Haze: 0.6 - 9.0
adhesion of coating	Folex method	passed
<b>Chemical</b>		
Chemical stability	Folex method	good
<b>Electrical</b>		
Dielectric strength <sup>1</sup>	ASTM D149	16,5 kV (0,13mm)/ 19,0 kV (0,18mm)

Thermal		
Shrinkage TD	130°C 30 min Folex method	< 0,5%
Shrinkage MD	130°C 30 min Folex method	< 1%
Maximum processing temperature		120°C
Max. use temp		45°C/ 80°C (with embossing/ without embossing) <sup>2</sup>
Min. use temp		0°C/ -20°C (with embossing/ without embossing) <sup>2</sup>
Melting temperature <sup>1</sup>	ASTM E794-85	255°C
Surface		
Roughness Ra	EN ISO 4287, ASME B46.1	0.04 - 0.25 µm
Pencil hardness	Folex method	3 H
Scratch resistance	Folex method	very good
Surface tension front side	DIN 53364, ASTM D2578	35 - 38 mN/m
Surface tension reverse side	DIN 53364, ASTM D2578	44 - 48 mN/m

<sup>1</sup> Data derived from base film Polyester manufacturers literature for base film

<sup>2</sup>at 50% RH without condensation, based on the recommendation of the "Fachgemeinschaft Eingabesysteme", they recommend max. 70°C

#### Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.