

DATA SHEET 22208.210.30700

DIALUX SI 208

Translucent polyester film, printable on one side for light boxes and other backlit displays.

Printing Systems



Rolls

| Art.Number | Width (mm) | Thickness | Length (m) |
|-----------------|------------|-----------|------------|
| 22208.210.39200 | 914 | 0.210 | 30 |
| 22208.210.30700 | 1067 | 0.210 | 30 |
| 22208.210.32200 | 1270 | 0.210 | 30 |
| 22208.210.33500 | 1370 | 0.210 | 30 |
| 22208.210.35200 | 1520 | 0.210 | 30 |

Technical data

Characteristic

- Extremely high colour density
- Brilliant, true colour reproduction with or without back lighting (Day&Night).
- Perfect flatness
- Very good temperature resistance

Finish

- Translucent, glossy

Specifications

| | |
|--------------------|----------|
| Coating Printsides | glossy |
| Width (mm) | 1067 |
| Thickness | 0,210 mm |

| | |
|------------------|-----------|
| Core Diameter | 76 mm |
| Length (m) | 30 |
| Opacity | 0,3 |
| Base Material | Polyester |
| Packing quantity | 1 roll |

Compatibility

- Useable on most large format Ink Jet printers using latex inks.
- Useable on most large format Ink Jet printers using solvent ink systems.
- Useable on most large format Ink Jet printers using UV curing ink systems.

Handling

- Note for Latex-Inks: To avoid the effect of rewetting (oil film on the print surface due to defective anchorage of ink) it is necessary to establish the optimal drying parameter. This can be done by means of print tests before production print. Rewetting can appear several days after printing when the drying conditions are defective. The rewetting can also be dependent on the given ambient conditions and the composition and consistence of the printing theme. When creating a media profile, this circumstance must be expressly taken into consideration.
- In regard to humidity: High air humidity during the printing process may lead to banding in the direction of printing and to striations in the print image caused by the transport or press rolls.
- Note for temperature setting: Before printing you must check that the correct drying temperature has been set by carrying out a trial print. Too high drying temperatures can lead to a deformation of the film which can later cause further problems while processing.
- Note for Drying time / Processing: The VOC which are contained in solvent and latex inks must be fully dried before further processing. For this reason it is necessary to take long enough drying times into account. The drying time of the printed media depends very much on the quantity of solvent applied. When printing the film in a roll-to-roll process, the printed strip must be unrolled and laid flat as soon as possible until final drying. Solvent residues due to insufficient drying times can lead to blocking during transport in rolled-up form. During lamination such residues can negatively impact the quality of the finished product (flatness, shrinkage behaviour, anchorage, etc...).
- The printed surface must be protected if it is subject over a long time to humidity, abrasion, sweat or other mechanical influences. In the case of un laminated prints, contact between the print side and the protective screen should be avoided.
- We recommend to use self-adhesive laminating foils for cold lamination or appropriate liquid lamination products.

Storage

- Shelf life: 1 year after delivery
- After printing the remaining roll must be removed from the plotter and stored in its closed original packing in a cool and dry environment.

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.